

## Derilux Silikon

Topcoat on a special phenylmethylpolysiloxan resin basis

- Field of application**
- Protection against corrosion for steel, aluminium and blasted high grade steel for high temperature areas.
  - One layer system for a lower rust protection requirement

- Product properties**
- Contents silicon
  - Resistance to light acids
  - Resistance to weak bases
  - Resistance to condensation
  - Coating systems for corrosivity category C4
  - Coating systems for high temperatures
  - Fast drying
  - Recoatable with itself

### Technical Specification

Colours	<b>RAL 5001</b> , RAL 9005. Other colours upon request. Colour deviation (Colour deviations may occur in the range of high temperatures due to the restricted temperature resistance of the pigments)
Flash point	>23 °C
Temperature stability	Up to 400 (short-term up to 450) °C
Gloss	Silky mat
Potential dry film thickness in one working process	Up to 40 µm
Viscosity	Appr. 65 sec running time (DIN 4 mm pot)
Density in kg/l	1,43
Solid content in %	67
Solid volume in %	46
Theoretical spreading capacity	<ul style="list-style-type: none"> <li>• 11,5 m²/l at 40 µm DFT</li> <li>• 8,04 m²/kg at 40 µm DFT</li> </ul>
Recommended film thickness	100 µm WFT corresponds to 50 µm DFT
Drying (DIN EN ISO 1517)	30 µm DFT
Dust-dry (Tg1)	After 20 min
Touch-dry (Tg4)	After 35 min
Dry (Tg6)	After 45 min
Accelerated drying	30 min., required at least 180°C
Interval for overcoating	<ul style="list-style-type: none"> <li>• after 3 h with itself without accelerated drying</li> </ul>
Note	<ul style="list-style-type: none"> <li>• The specifications are based on standard atmospheric conditions 23/50, DIN 50014.</li> <li>• Lower temperatures and/or higher humidity will prolong drying and hardening.</li> </ul>

### Safety information (See Security Data Sheet)

VOC-level	Appr. 474 g/l
Solvent content	Appr. 33 % by weight
Aromatic content	Appr. 30 % by weight

### Storage

- Storage
- In dry, cool rooms, if possible frost-proof
  - Ensure good ventilation

## Derilux Silikon

Shelf life	<ul style="list-style-type: none"> <li>6 month from date of delivery when in unopened original containers in cool and dry conditions</li> </ul>
<b>Application methods</b>	
Airless spraying	<ul style="list-style-type: none"> <li>Flow pressure 150 - 180 bar</li> <li>Nozzle size 0,009 - 0,011 inch (0,23 - 0,28 mm)</li> <li>Spraying angle according to the geometry and size of the object to be laquered</li> </ul>
Compressed air spraying	<ul style="list-style-type: none"> <li>Spraying pressure 4 - 5 bar</li> <li>Nozzle size 1,2 - 1,5 mm</li> </ul>
Electrostatic application	<ul style="list-style-type: none"> <li>Application is not possible</li> </ul>
Dipping	<ul style="list-style-type: none"> <li>Can not be applied as delivered</li> </ul>
Other methods	<ul style="list-style-type: none"> <li>Roller and brush application for repair work is possible</li> </ul>
Thinner	<ul style="list-style-type: none"> <li>Max. 5% Derozink-Verdünnung</li> </ul>
Cleaning	<ul style="list-style-type: none"> <li>Residues are dissolvable with Derozink-Verdünnung</li> </ul>
<b>Preparation of support</b>	<ul style="list-style-type: none"> <li>Shot blasting to a purity according to SA 2½</li> <li>Clean primer of the coating system</li> </ul>
<b>General remarks</b>	<ul style="list-style-type: none"> <li>During coating and drying the humidity should be min. 10 % / max. 85 %</li> <li>During coating and drying the environmental temperature should be min. 5°C / max. 30°C</li> <li>Object temperature at least 3° C above dew point.</li> </ul>
<b>Example for a system</b>	<ul style="list-style-type: none"> <li>Primer coat: Derogrund Silikon</li> <li>Finish coat: Derilux Silikon</li> </ul>

*The general information and descriptions contained in this specification are provided to the best of our knowledge. Our information and specifications do not constitute warranted characteristics in the legal sense. Any advice for preparation and application which may be provided verbally, in writing or by means of experiments is of general nature only, and any property rights of third parties are also to be regarded in this context. Our general instructions do not release you from your obligation to check the suitability of the products supplied by our company for the intended methods and purposes of application. Particular in those cases when our supplied material will be applied with products from other sources. The products are prepared, applied and used outside of our sphere of control and thus fall solely within the user's scope of responsibility.*

*Our general terms of sale and delivery apply as agreed.*

Product group: SD1001500100