

2K-Deripox Grund BBV 687.

Two component primer with active anti-corrosive pigments (zinc-phosphate and zinc-oxide) on epoxy resin basis, chemical cured with polyamine adduct

- Field of application**
- Systems for corrosion protection according to the German TL/TP-Korr steel construction specification
 - Primer for high rust protection requirements, as well for zinc surfaces
 - Product is certificated to sheet 87 of the German TL/TP- Korr steel construction specifications

- Product properties**
- Resistance to chemicals (on request)
 - Resistance to mineral oils
 - Recoatability: with epoxy paints (2K Deripox)
 - Recoatability: with polyurethane paints (2K Derocryl)

Technical Specification

Colours	RAL 1002 (687.02) , RAL 8012 (687.06).
Flash point	>23 °C
Temperature stability	Up to 200 (short-term up to 250) °C
Gloss	Silky mat
Potential dry film thickness in one working process	80 up to 100 µm
Mixing ratio	Hardener HL 500
(Basis:hardener) by weight	6:1
(Basis:hardener) by volume	3,5:1
Pot life in hours	12
Viscosity	Thixotrope
Density in kg/l	1,5
Solid content in %	73
Solid volume in %	54
Theoretical spreading capacity	<ul style="list-style-type: none"> • 6,75 m²/l at 80 µm DFT • 4,5 m²/kg at 80 µm DFT
Recommended film thickness	150 µm WFT corresponds to 80 µm DFT
Drying (DIN EN ISO 1517)	80 µm DFT
Dust-dry (Tg1)	After 50 min
Touch-dry (Tg4)	After 3 h
Dry (Tg6)	After 5 h
Cured chemically	After 7 days
Interval for overcoating	<ul style="list-style-type: none"> • after 24 h with two component Derocryl topcoats • after 6 h with two component Deripox topcoats • Max. after 12 months without slightly sanding
Note	<ul style="list-style-type: none"> • The specifications are related to the prepared mixture and are based on standard atmospheric conditions 23/50, DIN 50014. • Lower temperatures and/or higher humidity will prolong drying and hardening. • Application below +5 °C is not possible. • Using winter quality application is possible nearly to frost temperature. Application only on steel supports possible.
Safety information (See Security Data Sheet)	
VOC-level	Appr. 421 g/l

2K-Deripox Grund BBV 687.

Solvent content Appr. 27 % by weight

Aromatic content Appr. 24 % by weight

Storage

Storage • In dry, cool rooms, if possible frost-proof
 • Ensure good ventilation

Shelf life • 6 month from date of delivery when in unopened original containers in cool and dry conditions

Application methods

Mixing ratio • Stirr homogeneous, preferably with mechanical stirrer
 • Mix base paint and hardener according to the mixing ratio as specified

Airless spraying • Flow pressure 180 bar
 • Nozzle size 0,013 - 0,015 inch (0,33 - 0,38 mm)
 • Spraying angle according to the geometry and size of the object to be laquered
 • If required (two component: after mixing) using 5% Deripox-Verdünnung (687.150) is possible

Compressed air spraying • Spraying pressure 5 - 6 bar
 • Nozzle size 1,8 - 2,2 mm
 • Adjust to spraying viscosity (appr. 60 s DIN 4 mm) adding appr. 10 % Deripox-Verdünnung (687.150) (two component products: after mixing)

Electrostatic application • Application is possible provided that the material is diluted

Dipping • Can not be applied as delivered

Other methods • Roller and brush application is possible in the quality as delivered

Thinner • Max. 10% Deripox-Verdünnung (687.150)

Cleaning • Rinse immediately with Deripox-Verdünnung (687.150)

Preparation of support • Shot blasting to a purity according to SA 2½
 • If necessary clean with high pressure-cleaner and turbo-cleaner-solution
 • Sweeping for zinced supports
 • Mill scale, welding residues, dust, soluble residues from chemical pretreatments and zinc reaction products which might reduce adhesion have to be carefully and thoroughly removed

General remarks • During coating and drying the humidity should be min. 10 % / max. 85 %
 • During coating and drying the environmental temperature should be min. 5°C / max. 30°C
 • Object temperature at least 3° C above dew point.

Example for a system • Primer coat: 2K-Deripox Grund BBV 687.
 • Intermediate coat:
 • Finish coat: 2K-Derocryl Lack 687.

The general information and descriptions contained in this specification are provided to the best of our knowledge. Our information and specifications do not constitute warranted characteristics in the legal sense. Any advice for preparation and application which may be provided verbally, in writing or by means of experiments is of general nature only, and any property rights of third parties are also to be regarded in this context. Our general instructions do not release you from your obligation to check the suitability of the products supplied by our company for the intended methods and purposes of application. Particular in those cases when our supplied material will be applied with products from other sources. The products are prepared, applied and used outside of our sphere of control and thus fall solely within the user's scope of responsibility.

Our general terms of sale and delivery apply as agreed.

Product group: EG0990100220